



Product Data Sheet

Super Red Tacky EP-2 Lithium Grease

Made In USA

Product Description

Super Red Tacky is ideally suited for applications in which heavy shock loading is encountered, the combination of polymers and heavy base oil viscosity makes this grease ideal. In addition it can be used in rolling contact with bearings in electrical motors, blowers, centrifugal pumps, etc., where a high quality grease is desired. Also in rolling contact and plain sleeve bearings used under unfavourable environmental conditions involving moisture, high loads and or high temperatures, such as jaw crushers, tube mills, mining, material processing, cement and aggregate industries. The polymer additive ensures that the grease will stay where it is applied.

Package Information

180KG Drum, 20KG Tub, Carton of 20 450gsm Cartridges.

The Oilman Group Pty Ltd
www.oilman.com.au

Head Office: (08) 8262 9399
Adelaide: (08) 8349 9277
Brisbane: (07) 3216 7196

Typical Characteristics

| | |
|--|--------------|
| NLGI Grade | 2 |
| Soap Type | Lithium |
| Texture | Smooth/Tacky |
| Worked Penetration, ASTM D-217, 60 strokes | 265-295 |
| Dropping Point, ASTM D-2265, °C (°F) Min | 176.6 (350) |
| Oxidation Stability, ASTM D-942 PSI Drop | 10 Max |
| Wheel Bearing Leakage, ASTM D-1263 Gms | 5 |
| Rust Test, Bearing Corrosion, ASTM D-1743 | Pass |
| Water Wash-Out, ASTM D-1264, 79.4°C | 10% Max |
| Timken OK Load, LB ASTM D-2509 | 60 Min |
| Four Ball EP Test, ASTM D-2596 | |
| Weld Point, KG | 250 Min |
| LWI | 40 |
| Four Ball Wear, ASTM D-2266, Scar Dia. Mm, 40 KG | 0.60 |
| Base Oil Viscosity | |
| 100°C, cSt | 26-28.5 |
| 40°C, cSt | 390-450 |
| 100°F, SUS | 2,100-2,300 |
| Viscosity Index Min | 85 |
| Pour Point °C | 0 |

Typical Characteristics are average values, and may vary due to normal manufacturing tolerances. The information contained herein is subject to change without notice.